

Technical Data Sheet HS-760

Product Description

Redispersible VAE powder HS-760 is a product made of vinyl acetate-ethylene (VAE) copolymer emulsion as the main component, via spray drying process into flowable white polymer powder, which can be widely used for dry mixed mortar or powder construction material products.

Product Property

- HS-760 as a VAE polymer powder can be redispersed well into polymer emulsion again after mixing with water.
- HS-760 with the characteristics of high ethylene content and low film forming temperature, therefore, can form very soft film, which fits for application scenarios that require high flexibility or good adhesion to organic interfaces.
- HS-760 with good acid and alkaline resistance, is good for the workability and weatherability of the construction material products which used it.
- HS-760 with good and wide compatibility, can use with almost all other chemical additives in diverse formulations.
- HS-760 not only retains the superior performances of the original VAE emulsion, such as good film formation, excellent adhesion and durable flexibility, but also improves the convenience and stability for transportation, storage and operation.
- HS-760 is produced without adding plasticizer, film forming additives or solvent, so it has excellent environmental protection, low odor, low VOC.

Redispersible VAE Powder



Technical data

Property	Method	Result
Appearance	Visual	White powder
Solid content	GB/T 29594	≥98.0%
Ash content	GB/T 29594	11±2%
Bulk density	GB/T 29594	400~600 g/L
Tg	Hongshi method	Approx.-10°C
MFPT	Hongshi method	0°C
>450μm	Hongshi method	≤2.0%

Applications and dosage

HS-760 is recommended to use in dry mixing mortar or powder construction material products, such as ceramic tile adhesive (S1, S2), external wall insulation system (EIFS/ETICS), extrusion mortar for EPS component, skim coat, sound insulation mortar, Joint compound, etc.

Normally recommended dosage is 0.5~5% in total formulation.

- In EIFS/ETICS formulation, is recommended to add 2~4% dosage of HS-760, which can effectively improve the bonding strength, impact resistance and reduce water absorption.
- In flexible skim coat formulation, is recommended to add 3~5% dosage of HS-760, which can significantly improve the flexibility, and bonding strength with the substrate.
- In flexible ceramic tile adhesive (S1, S2) formulation, is recommended for add 5~10% dosage of HS-760 to improve the flexibility, and bonding strength of ceramic tiles.

Storage

- HS-760 storage should protect from moisture.
- At storage temperatures above 30°C or under pressure during storage may cause HS-760 caking occurs.
- If HS-760 is not used up after opening, it should be sealed in time and used as soon as possible.
- The optimal service life of HS-760 is 12 months, and the possibility of the product performances beyond the best use period will be reduced.



Redispersible VAE Powder

- In order to ensure the best use effect of HS-760, it is recommended to test the product's performances before use.

Packaging

- 25Kg bag
- 600Kg Big Bag

Transportation

Ensure that the packaging is intact during transportation, protects from moisture, avoids high temperature and pressure.

This information is based on the description of the product and its current knowledge of the product in consideration of the need for safe use. But these data do not serve as a guarantee for some specific application scenarios. It is the responsibility of the product user to ensure that the formulation is suitable for the purpose of its use. Hongshi is not responsible for any risk arising from such information. At the same time, according to the needs of product development and technological progress, Hongshi will reserve the right to update the product data. (11-2024)